

	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
<b>PRODUCT DESCRIPTION</b>				
Traitement de Surface	-	-	-	<b>Protectorsol</b> <small>TRIPLE ACTION</small>
Complexe de Surface	-	-	-	<b>D-Max+</b> <small>DURABILITY</small>
Mousse	-	-	-	<b>CXP HD</b> <small>COMFORT</small>
Epaisseur	EN 428	-	mm	<b>6.2 mm</b> 
Poids	EN 430	-	kg/m <sup>2</sup>	4.2
Longueur	EN 426	-	lm	20.5 Standard
Largeur	EN 426	-	lm	1.5
Impact Protection Index	AC- P90-205	-	%	<b>IPI = 52%</b>
<b>SPORT PROPERTIES</b>				
Shock absorption	EN 14808	≥ 25	%	
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 2
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 à 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 à 65	cm	-
	ITF	-	-	-
<b>TECHNICAL CHARACTERISTICS</b>				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.25
<b>CLASSIFICATION</b>				
Fire	EN 13501-1	-	-	
Treatment	-	-	-	<b>Sanosol</b> <small>HYGIENE</small>
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99.9 % inhibits growth
<b>DECLARATION OF PERFORMANCE</b>				
	DOP-005-1011-A	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	METHODE D'INSTALLATION		
	Recommandation GERFLOR	Unité	Résultat
Glued installation: "Original"	Level of dampness of the subfloor	%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolsport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% humidity (CCM)

**COLOUR RANGE**




8840 Wood Black



4331 Wood Natural



3708 Wood Grey



4453 Wood Blue



4506 Wood Green



8068 Wood Chocolate

TARAFLEX™ MULTI-USE 6.2



(3) The implementation of an effective cleaning method is the best defence against infection