



PRODUCT CHARACTERISTICS				
	Standard	Requirement	Unit	Results
<b>PRODUCT DESCRIPTION</b>				
Surface treatment	-	-	-	<b>Protectsol</b> <sup>TRIPLE ACTION</sup>
Surface complex	-	-	-	<b>D-Max</b> <sup>DURABILITY</sup>
Foam	-	-	-	<b>CXP HD</b> <sup>COMFORT</sup>
Thickness	EN 428	-	mm	<b>7 mm</b>
Weight	EN 430	-	kg/m <sup>2</sup>	4.6
Length	EN 426	-	lm	26.4 max
Width	EN 426	-	lm	1.5
Impact Protection Index	AC- P90-205	-	%	<b>IPI = 73%</b>
<b>SPORT PROPERTIES</b>				
Shock absorption	EN 14808	≥ 25	%	<b>P1</b>
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 2
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
<b>TECHNICAL CHARACTERISTICS</b>				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
<b>CLASSIFICATION</b>				
Fire	EN 13501-1	-	-	<b>Cl-s1</b>
Treatment	-	-	-	<b>Sanosol</b> <sup>HYGIENE</sup>
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99.9 % inhibits growth
<b>DECLARATION OF PERFORMANCE</b>				
<b>CE</b>	DOP-005-1013-A	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

INSTALLATION METHODS			
	Gerflor's recommendation	Unit	Results
Glued installation: "Original"	Level of dampness of the subfloor	%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% humidity (CCM)

**COLOUR RANGE**

○ Standard roll 20.5 ml

TARAFLEX™ SPORT M EVOLUTION

(3) The implementation of an effective cleaning method is the best defence against infection

