


| DESCRIPTION | Standard | Requirement | Units | Results |
|---|--------------------|-------------|-------------------|---|
| Dry-Tex System | | | | |
| Eco-fit System | | | | |
| PRODUCT DESCRIPTION | | | | |
| Surface treatment | - | - | - | Triple-Action Protocolsol® |
| Surface complex | - | - | - | D-Max™ |
| Foam | - | - | - | - |
| Thickness | EN 428 | - | mm | 2.1 |
| Weight | EN 430 | - | kg/m ² | 2,9 |
| Length | EN 426 | - | lm | 30 Max |
| Width | EN 426 | - | lm | 1.5 |
| SPORT PROPERTIES | | | | |
| Shock absorption | EN 14808 | ≥25 | % | - |
| Vertical deformation | EN 14809 | ≤3.5 | mm | - |
| Energy return | NF P 90 203 | ≥ 0.31 | m/s | - |
| Sliding coefficient | EN 13036-4 | 80 to 110 | - | 80 - 110 |
| Ball bounce | EN 12235 | ≥ 90 | % | ≥ 90 |
| Ball speed | UEFA | 50 to 65 | cm | - |
| | ITF | - | - | - |
| TECHNICAL CHARACTERISTICS | | | | |
| Abrasion resistance | EN ISO 5470-1 | ≤ 1000 | mg | ≤ 350 |
| Impact resistance | EN 1517 | ≥ 8 | N/m | ≥ 8 |
| Indentation resistance | EN 1516 | ≤ 0.5 | mm | ≤ 0.5 |
| CLASSIFICATION | | | | |
| Fire | EN 13501-1 | - | - | Bfl-s1 |
| Special treatment | - | - | - | Sanosol® |
| CE MARKING | | | | |
|  | EN 14 904 :2006 | - | - | Fire Sliding Coefficient Abrasion Resistance Resistance to roaling load |